



## TECHNICAL SPECIFICATION SHEET

Range

Arlan

Design

Slub Effect Chenille

Composition  $\pm 3\%$  per compound

100% Polyester

Useable Fabric Width (cm)

138

Pattern Repeat (cm)

Vertical	N/A	Horizontal	N/A
----------	-----	------------	-----

Martindale (rubs)

100,000

Seam (mm)

Warp	$\leq 3\text{mm}$	Weft	$\leq 2\text{mm}$
------	-------------------	------	-------------------

Tensile (N)

Warp	$\geq 1500\text{N}$	Weft	$\geq 750\text{N}$
------	---------------------	------	--------------------

Tear (N)

Warp	$\geq 150\text{N}$	Weft	$\geq 45\text{N}$
------	--------------------	------	-------------------

Pilling Grade

@2000 rubs	4	@5000 rubs	4
------------	---	------------	---

Bursting (kPa)

n/a

Weight (gsm)  $\pm 5\%$

520

FR Weight (gsm)  $\pm 5\%$

UK	620	SIAN	620
----	-----	------	-----

FR Chemical Reference

UK	GreenFR®	SIAN	GreenFR®
----	----------	------	----------

Care Instructions

Professional dry clean in situ only

